

# BETASEAL™ 1527EP

## Glass Bonding Systems

BETASEAL™ 1527EP is a medium viscosity, high modulus, non conductive, fast curing glass bonding adhesive which requires a primer during the process.

It is a one component, ambient moisture curing adhesive for direct glazing applications. It shows excellent sag and bead stability. Skin formation and curing are dependent on humidity, temperature and application dimension. BETASEAL™ 1527EP has a 1 hour Safe-Drive-Away-Time, crash tested to FMVSS 212 specification with twin airbags.

All DuPont Adhesives products are primarily developed in co-operation with the automobile manufacturers, according to their needs and their specifications, they are approved for the specific applications as defined by the customer. The use of the product other than approved application must be released in written form by the Technical Service of DuPont Adhesives.

Unless specified otherwise test are conducted at 23°C/50% relative humidity.

### Product information

Colour	Black	
Basis	Polyurethane - prepolymers	
Density	1.28 - 1.32 g/cm <sup>3</sup>	ISO 845
Solid content	≥95 %	

### Uncured properties

Skinning time	8 - 15 min
Cure rate, after 24h	≥0.118 in
Sagging	30 <sup>[1]</sup> °

[1]: On vertical wall tilting (maximum).

### Rheological properties

Extrusion Viscosity	288 - 416 <sup>[2]</sup> s
---------------------	----------------------------

[2]: 23°C, 4mm / 4bar

### Application technique

Ambient Temperature at application	14 - 104 °F
Surface Temperature at application	14 - 104 °F
Adhesive Temperature at application	41 - 113 °F

### Cured properties

Temperature stability	-40 - 212 °F
Volume resistivity	1E10 Ohm.cm



# BETASEAL™ 1527EP

## Glass Bonding Systems

### Typical mechanical properties

Stress at break	725 psi	ISO 1798
Strain at break	350 %	ISO 1798
Shear modulus	261 - 406 psi	
Lap shear strength, 3 days	≥508 psi	DIN EN 1465
Shore hardness A	55 - 65 -	DIN 53505

### Storage and stability

Shelf life 9<sup>[3]</sup> months

[3]: Shelf life is assured at +5°C to +25°C in unopened containers. Short term storage temperatures: 0°C to +40°C. Minimum shelf life upon dispatch from DuPont production location.

### Characteristics

Compatibility Glass, Paint

### Additional information

Adhesives

### Bonding surface preparation

All bonding surfaces must be free of impurities (dirt, dust, water, oil, grease, release agent and similar contaminants). In general surfaces should be primed. Verify compatibility or consult our technical service department.

### Application Equipment

Cartridges, Sausages: Application with a standard 1-component hand-operated, pneumatic or electrical gun with piston bar (no direct air guns!).

Drums, Pails: Robotic pump system possible.

Upon request our application specialists can give support to select the right application system for your application.

### Cleaning

Uncured adhesive residues can easily be removed with BETACLEAN™ 3500. Hardened adhesive residues can only be removed mechanically. Immerse equipment in BETACLEAN™ 3000.



# BETASEAL™ 1527EP

## Glass Bonding Systems

Revised: 2021-07-21

Page: 3 of 3

[dupont.com](http://dupont.com)

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

**CAUTION:** Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2022 DuPont. All rights reserved.